

Our Ref: SW/LS/GL

3 June 2017

Report 297933

Page 1 of 3

Luxury Contract Furnishings Limited
Ladywell Mills
Hall Lane
Bradford
BD4 7DF

Contact: Dairine

DATE RECEIVED	: 23 MAY 2017
QUALITY/REFERENCE	: 4546 EXHILIRATE
REPUTED FIBRE CONTENT	: 90% WOOL, 10% NYLON
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: MULTI STRIPE
PERFORMANCE STANDARD	: GENERAL

REQUEST: Colour fastness to light, wet & dry rubbing, resistance to pilling & abrasion, seam slippage, tensile strength and tear strength

COMMENTS: Flammability to follow on report 297933/2



S. WISEMAN
LABORATORY DIRECTOR

L. SHERIDAN
LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.



118 Lupton Avenue Leeds LS9 6ED
Tel: 0044 (0) 113 248 8830 Fax: 0044 (0) 113 248 0239 Email: hstts@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

3 June 2017

Report 297933

Page 2 of 3

COLOUR FASTNESS TO:

BS EN ISO 105-X12:2016 Rubbing

Colour	Test	Staining
	Dry, Face, Length	4-5
	Dry, Face, Width	4-5
	Wet, Face, Length	4-5
	Wet, Face, Width	4-5

BS EN ISO 105-B02:2014 Light Fastness Blue Wool 6

	Shade change
Cerise	6
Orange	6
Navy	6+
Teal	5-6
Blue	5-6
Lime	6

PHYSICAL

BS EN ISO 13936-2:2004 Seam Slippage

	Length	Width
Seam opening at 180 N	6.0 mm	1.6 mm

BS EN ISO 13934-1:2013 Tensile Strength 50mm Strip

	Length	Width
Mean	612.1 N	414.0 N



118 Lupton Avenue Leeds LS9 6ED
 Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: hstts@hstts.co.uk
 Registered No. 2899980 VAT No. 613 4310 86

3 June 2017

Report 297933

Page 3 of 3

PHYSICAL

BS EN 13937-3:2000 Wing Tear Strength

	Length	Width
Mean	44.1 N	36.1 N

BS EN ISO 12945-2:2000 PILLING MODIFIED MARTINDALE

Revs	Grade
500	4-5
1000	4-5
2000	4-5
5000	4

Sample tested: As Received

Sample tested against Wool abradant as specified in BS EN ISO 12947.

BS EN 14465:2003 Annex A Abrasion Resistance

12 kPa load. End point: 3 threads broken (Upholstery woven)

Number of rubs to breakdown:
Head 1 80,000
Head 2 80,000
Head 3 80,000
Head 4 80,000