



Our Ref: SW/NW

<u>Report 400917</u>

Luxury Contract Furnishings Limited T/A Abbotsford Textiles Ladywell Mills Hall Lane Bradford BD4 7DF

Contact: Caroline Doyle

DATE RECEIVED
QUALITY/REFERENCE
REPUTED FIBRE CONTENT
FABRIC DESCRIPTION
COLOUR/DESIGN
ORDER NUMBER

21 DEC 2022
COUNTRY CLASSICS
100% BRITISH WOOL
WOVEN
GREEN CHECK
POLCF2200654

PERFORMANCE STANDARD

TEST PERFORMANCE DATE(S)

: BS2543:2004 & BS EN 14465:2003 + A1:2006

: 21/12/2022 - 03/01/2023



COMMENTS: Flammability to follow on report 400917/2.

REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Abrasion of upholstery	BS EN ISO 12947-2: 1998 /	Pass		Level B suitable for General
	BS EN 14465: 2003 Annex			Contract
	A Abrasion Resistance			



118 Lupton Avenue Leeds LS9 6ED Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk Registered No. 2899980 VAT No. 887127683

3 January 2023

Page: 1 of 4



Modern Testing Services



3 January 2023

Page: 2 of 4

Report 400917

Mara.

S. WISEMAN LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.

Conformity statements for tests marked \ddagger are subject to the application of the decision rules set out in Annex A of this report and information on the measurement uncertainty for the relevant test(s) is provided within this test report.



118 Lupton Avenue Leeds LS9 6ED Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk Registered No. 2899980 VAT No. 887127683





3 January 2023

Page: 3 of 4

<u>Report 400917</u>

PHYSICAL

BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A Abrasion Resistance 12 kPa load.

Number of rubs to breakdown:		Level B suitable for
Head 1 30,000		General Contract
Head 2 30,000		
Head 3 30,000		
Head 4 30,000		
Shade change after 3,000 rubs:	Grade 4-5	

Tests indicated § are within the bounds of the flexible scope of accreditation operated by the laboratory.



118 Lupton Avenue Leeds LS9 6ED Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk Registered No. 2899980 VAT No. 887127683





3 January 2023

Report 400917

Page: 4 of 4

ANNEX A: DECISION RULES

In accordance with the requirements of BS EN ISO 17025:2017 it is necessary for the decision rules applied to each test carried out to be agreed with the customer and reported. The following decision rules have been applied by default unless stated to the contrary in this test report.

Rule 1	Applicable to any requirement stated to be 'Minimum xxxx' or 'Maximum xxxx' or stated to be a range (e.g. XXX to YYY or AAA \pm B):
	The use of constrained simple acceptance based on the difference between a stated limit (requirement) and the reported test result being greater than the measurement uncertainty (U) for a conformity probability of 95%. The risk of false accept or false reject is 2.5%
Rule 2	For tests based on subjective grading of a result using a 9-point scale (e.g. colour fastness, pilling, etc):
	Simple acceptance based on the test uncertainty ratio (T.U.R.) being <4. The risk of false accept or false reject is up to 50% but will be reduced the further the reported result is away from the stated requirement.
Rule 3	For tests based on a subjective assessment of a property (e.g. whether a component detaches or not):
	Simple acceptance based upon the conditions of testing falling within the criteria for test set out in the test method within a conformance probability of 95%. The risk of false accept or false reject of the testing conditions not meeting the specified requirements is 2.5%.
Rule 4	If a validated test method (e.g. BS EN ISO standard) indicates that the measurement uncertainty has already been taken into account when calculating the test result then results may be reported using simple acceptance without the need for the application of the relevant decision rule set out above.

Any decision rule proposed by the client must satisfy the requirements of ISO 17025:2017 to include consideration of the measurement uncertainty and has been included within the test report. The company is obliged to refuse to apply decision rules that do not satisfy the requirements of BS EN ISO 17025:2017.



118 Lupton Avenue Leeds LS9 6ED Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk Registered No. 2899980 VAT No. 887127683