

Our Ref: LAS/RM

11 October 2022

**Report 397535/7****Page 1 of 3**

Luxury Contract Furnishings Limited  
T/A Abbotsford Textiles  
Ladywell Mills  
Hall Lane  
Bradford  
BD4 7DF

Contact: Caroline Doyle

---

DATE RECEIVED	:	28 SEPTEMBER 2022
DATE TESTED	:	11 OCTOBER 2022
MANUFACTURER	:	NOT GIVEN
SUPPLIER	:	ABBOTSFORD TEXTILES
TYPE OF FURNITURE	:	SEATING CONTRACT
PRODUCT NAME/ ID	:	A509 CLASSIC PLAIN
REPUTED FIBRE CONTENT	:	100% FR POLYESTER
COMPOSITION OF WEAVE	:	PLAIN WEAVE
DENSITY (THREADS PER INCH)	:	WARP: 8.5, WEFT: 7.5
YARN NUMBER COUNT	:	NM 6.70
FABRIC THICKNESS (MM)	:	2MM
FABRIC WEIGHT (G/M <sup>2</sup> )	:	280
COLOUR/ DESIGN	:	VARIOUS
FIRE RETARDANT	:	INHERENT

---

REQUEST: IMO FTP Code 2010 – International Code for Application of Fire Test Procedures  
Annex I: Part 8 – Test for Upholstered Furniture.

---

RESULT: The sample submitted, when tested as described, complies with the requirements of  
the IMO FTP Code 2010 Annex 1: Part 8

---



**R. MASKILL**  
**FLAMMABILITY TECHNOLOGIST**



**L. SMITH**  
**QUALITY COORDINATOR**

This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



1695

Our Ref: LAS/RM

11 October 2022

**Report 397535/7**
**Page 2 of 3**
**IMO FTP Code 2010 – International Code for Application of Fire Test Procedures  
 Annex I: Part 8 – Test for Upholstered Furniture**
**Procedure**

Specimens were tested in the ‘as received’ condition after being conditioned for 72 hours in an indoor ambient atmosphere followed by a minimum of 16 hours in an atmosphere of  $(23 \pm 2)^{\circ}\text{C}$  and  $(50 \pm 5)\%$  relative humidity.

Tests were made in accordance with part 8 of the 2010 FTP code. The specimens were mounted over filings of combustion modified high resilience foam with a density of approximately  $35\text{-}36\text{ kg/m}^3$ . The smouldering cigarettes used were NIST standard reference material 1196a reduced to  $(70 \pm 4)\text{mm}$  in length.

**Requirements**

Smouldering Cigarette No flaming or progressive smouldering shall be observed within 1 hour after the placement of the smouldering cigarettes.

Flame Ignition Source All flaming and smouldering shall cease within 120 seconds after the removal of the flaming ignition source.

**Results**

The results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Parameter – Smouldering Cigarette	Test 1	Test 2	Outcome
Progressive smouldering observed within 1 hr	No	No	Pass
Extent of damage to the specimen [mm]	20 (vertically)	17 (vertically)	

Parameter – Flaming Ignition	Test 1	Test 2	Outcome
Duration of flaming [sec]	0	0	Pass
Smouldering observed after 120 seconds	No	No	
Extent of damage to the specimen [mm]	64 (vertically)	68 (vertically)	

Our Ref: LAS/RM

11 October 2022

**Report 397535/7****Page 3 of 3****Decision rules**

The decision rule applicable to statements of conformity relating to the test(s) carried out is simple acceptance based on the measured test results not falling within a range either side of a specified limit that is equal to the uncertainty of measurement for the parameter measured (based on 95% confidence levels). In all other regards, the decision rule is based on simple acceptance predicated upon the conditions of testing falling within the criteria for test set out in the test method with a conformance probability of 95%. The risk of false accept or false reject is therefore not greater than 2.5%.

Uncertainty of measurement:	Timings	$\pm 0.4s$
	Dimensions	$\pm 0.5mm$

